

PMC 1290

Description PMC 1290 is a coextruded sheet comprised of an impact-modified, high gloss ASA cap over a

medium impact ABS core. This product is designed to offer a sheet that provides the impact toughness & outdoor weather resistance of ASA, with the ease of processing & bonding of ABS.

Applications Interior & exterior panels, dashes, consoles, covers, shrouds

| PROPERTY | TYPICAL VALUE ¹ | UNITS | TEST METHOD |
|--|--|----------------------|-------------|
| Specific Gravity | 1.12 | | ISO 1183 |
| Gloss, 60° (smooth, post-formed, male tooling) | 90 - 100 | % | ASTM 523 |
| Shrink Rate | 0.5 – 0.7 | % | ISO 294-4 |
| Flexural Modulus | 285,000 1,965 | psi MPa | ASTM D790 |
| Tensile Strength at Yield | 5,640 38.9 | psi MPa | ASTM D638 |
| Gardner at 73°F (23°C) Impact at 32°F (0°C) at -22°F (-30°C) | 320 (36) 312 (35) 302 (34) | in*lbs (Joules) | ASTM D5420 |
| HDT at 66 psi (0.45 MPa) at 264 psi (1.45 MPa) | 200 (93) 172 (78) | °F (°C) | ASTM D648 |
| CLTE (-30°C to 80°C) | 4.2 x 10 ⁻⁵ 7.6 x 10 ⁻⁵ | in/in/°F mm/mm/°C | ISO 11359 |

Property values tested on co-extruded sheet, 0.187" thick, 10% cap layer, up to 30% regrind used

NOTE: Data values are typical properties and are not to be construed as specifications. Users should confirm results by their own tests and evaluation methods. SIMONA PMC makes no warranties, expressed or implied, concerning the suitability of use. No freedom from infringement of any patent of others is to be inferred. SIMONA PMC reserves the right to make additions, deletions, or modifications to this information at any time without prior notification. Rev. 03.20

SIMONA PMC

2040 Industrial Drive Findlay, OH 45839 T: 877.289.7626 F: 419.425.0501 www.simona-pmc.com