

How to Thermoform TPO

Thermoplastic Polyolefins

GLOBAL THERMOPLASTIC SOLUTIONS

Thermoplastic Polyolefins (TPO) are elastomer-modified materials developed specifically for thermoformable sheet extrusion.

TPOs can be formed using most oven designed, but, for maximum control and performance, those having ceramic or quartz elements with multiple control zones are recommended.

The forming of TPOs on fully-automatic, multi-station machines may require longer heating times in order to compensate for longer cooling cycles typical of TPO. If cycle time is a concern, the use of cooling fixtures may allow for faster cycles.

General Thermoforming Start-Up Conditions for TPO

| Sheet Temperature, °F | 320-360 |
|-----------------------------------|----------|
| Tool Temperature, °F | 170-190 |
| Part Removal Temperature, °F | 140-170 |
| Minimum Vacuum, inches of Hg | 25 |
| Drying Temperature, °F (1-4 hrs.) | 120-180* |

*Normally, drying is not necessary. However, drying at the above conditions may lead to a better-looking surface finish and optimal sheet performance

TPO Thermoforming Best

| Tool Mounting | Top Platen |
|--------------------------------|---------------------------------|
| Plug Assist Material | Syntactic Foam |
| Oven Elements | Ceramic or Quartz / Multi-Zoned |
| Vacuum Actuation | Bleed in as tool hits sheet |
| Tool Finish | Vapor Honed / Sand Blast |
| Vacuum Hole Size | #60 – drill bit |
| Environmental Conditions | Controlled – no drafts |
| Cycle Time & Warpage Reduction | Cooling Fixtures |



CUSTOM EXTRUSION SOLUTIONS

TPO | ABS | Acrylic | ASA | PC/ABS | Soft-touch

SIMONA PMC | +1 877 289 7626 | info@simona-pmc.com | www.simona-pmc.com



LIMITED WARRANTY, WARRANTY DISCLAIMERS AND LIMITATIONS OF REMEDIES AND LIABILITIES.

Before using a SIMONA PMC product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the SIMONA PMC product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose.

In addition, no immunity under SIMONA PMC or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of SIMONA PMC except in a writing signed by an authorized SIMONA PMC employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at SIMONA PMC's option, and in no event shall SIMONA PMC be liable for special, consequential, incidental, punitive or exemplary damages.