

## **PMC® 1210**

**Description** PMC® 1210 is a coextruded sheet comprised of an impact-modified, low gloss acrylic cap over a medium impact ABS core. This product is designed to offer a sheet that provides the durability and outdoor weather resistance of acrylic, with the ease of processing and bonding of ABS.

Applications Interior and exterior panels, dashes, consoles, covers, shrouds

PROPERTY	TYPICAL VALUE <sup>1</sup>	UNITS	TEST METHOD
Specific Gravity	1.13		ISO 1183
Gloss, 60° (textured, post-formed, male tooling)	3 - 7	%	ASTM 523
Shrink Rate	0.5 - 0.7	%	ISO 294-4
Flexural Modulus	374,000 2,579	psi MPa	ASTM D790
Tensile Strength at Yield	6,048 41.7	psi MPa	ASTM D638
Gardner at 73°F (23°C) Impact at 32°F (0°C) at -22°F (-30°C)	282 (32) 267 (30) 107 (12)	in*lbs (Joules)	ASTM D5420
HDT at 66 psi (0.45 MPa) at 264 psi (1.45 MPa)	205 (96) 187 (86)	°F (°C)	ASTM D648
CLTE (-30°C to 80°C)	4.3 x 10 <sup>-5</sup> 7.7 x 10 <sup>-5</sup>	in/in/°F mm/mm/°C	ISO 11359

<sup>1</sup> Property values tested on co-extruded sheet, 0.187 in thick, 10% cap layer, up to 30% regrind used

**NOTE:** Data values are typical properties and are not to be construed as specifications. Users should confirm results by their own tests and evaluation methods. SIMONA PMC makes no warranties, expressed or implied, concerning the suitability of use. No freedom from infringement of any patent of others is to be inferred. SIMONA PMC reserves the right to make additions, deletions, or modifications to this information at any time without prior notification. Rev. 03.20

SIMONA PMC

2040 Industrial Drive Findlay, OH 45839 T: 877.289.7626 F: 419.425.0501 www.simona-pmc.com