



# PMC<sup>®</sup> 750

**Description** PMC<sup>®</sup> 750 is a coextruded, high melt strength, TPO sheet system with an olefinic high gloss cap layer with a broad processing window, and favorable mechanical properties.

**Applications** Exterior components, industrial covers, valences, claddings, rocker panels, shrouds, radomes

PROPERTY	TYPICAL VALUE <sup>1</sup>	UNITS	TEST METHOD
Specific Gravity	1.10		ISO 1183
Gloss, 60° (smooth, post-formed, male tooling)	85 - 90	%	ASTM 523
Shrink Rate	3.8 - 1.0	%	ISO 294-4
Flexural Modulus	290,800 2,006	psi MPa	ASTM D790
Tensile Strength at Yield	3,091 21.3	psi MPa	ASTM D638
Gardner Impact at 32°F (0°C) at -22°F (-30°C)	320 (36) 280 (23)	in*lbs (Joules)	ASTM D5420
Multi-Axial Impact at 32°F (0°C) at -22°F (-30°C)	44.0, 100% ductile 32.4, 50% ductile	Joules	ASTM D3762
HDT at 66 psi (0.45 MPa) at 264 psi (1.45 MPa)	212 (100) 134 (57)	°F (°C)	ASTM D648
CLTE (-30°C to 80°C)	3.3 x 10 <sup>-5</sup> 5.9 x 10 <sup>-5</sup>	in/in/°F mm/mm/°C	ISO 11359

<sup>1</sup> Property values tested on co-extruded sheet, 0.125 in (4 mm) thick, 10% cap layer, 30% regrind used

**NOTE:** Data values are typical properties and are not to be construed as specifications. Users should confirm results by their own tests and evaluation methods. SIMONA PMC makes no warranties, expressed or implied, concerning the suitability of use. No freedom from infringement of any patent of others is to be inferred. SIMONA PMC reserves the right to make additions, deletions, or modifications to this information at any time without prior notification. Rev 05.20

**SIMONA PMC**  
 2040 Industrial Drive  
 Findlay, OH 45839  
 T: 877.289.7626  
 F: 419.425.0501  
[www.simona-pmc.com](http://www.simona-pmc.com)



## PMC<sup>®</sup> 750 Electrical Properties<sup>2</sup>

Frequency (GHz)	Dielectric Constant (K)	Dissipation Factor (Df)	Method
2.5	2.55	0.006	CTG-TM-0100-2018
5.0	2.59	0.002	
6.0	2.59	0.004	
10.0	2.60	0.001	
18.0	2.59	0.004	
24.0	2.58	0.002	
28.0	2.58	0.000	
30.0	2.57	0.001	
39.0	2.58	0.003	

<sup>2</sup> Electrical properties tested on co-extruded sheet, 0.125 in (4 mm) thickness, 10% cap layer, 30% regrind used