



# Premier Cap®1620

**Description** Premier Cap® 1620 is a next-generation low gloss, coextruded TPO sheet system over a standard melt strength core. This product is designed to offer a weatherable cap that provides enhanced scratch and mar resistance over a cost-effective substrate, providing enhanced surface durability with improved economics.

**Applications** Exterior components, industrial covers, housings, claddings, shrouds

PROPERTY	TYPICAL VALUE <sup>1</sup>	UNITS	TEST METHOD
Specific Gravity	1.06		ISO1183
Gloss,60° (smooth, post-formed, male tooling)	14- 18	%	ASTM523
Crock Mar Resistance (Retained gloss at 60° observer)	70- 80	%	PMC Method
Shrink Rate	0.9- 1.1	%	ISO294-4
Flexural Modulus	250,000 1,724	psi MPa	ASTM D790
Tensile Strength at Yield	2,740 18.9	psi MPa	ASTM D638
Gardner Impact at 32°F (0°C) at -22°F (-30°C)	320 (36.2) 313 (35.0)	in*lbs (Joules)	ASTM D5420
Multi-Axial Impact at 32°F (0°C) at -5°F (-15°C) at -22°F (-30°C)	28.2, 100% ductile 41.0, 100% ductile 18.7, 0% ductile	Joules	ASTM D3762
HDT at 66psi (0.45MPa) at 264psi (1.45 MPa)	189(87) 118(48)	°F (°C)	ASTM D648
CLTE (-30°C to 80°C)	3.4x10 <sup>-5</sup> 6.9x10 <sup>-5</sup>	in/in/°F mm/mm/°C	ISO11359

<sup>1</sup>Property values test edonco extruded sheet, 0.125 in thick, 10% cap layer, 30% regrind

**NOTE:** Data values are typical properties and are not to be construed as specifications. Users should confirm results by their own test and evaluation methods. SIMONA PMC makes no warranties, express or implied, concerning the suitability of use. No freedom from infringement of any patent of others is to be inferred. SIMONA PMC reserves the right to make additions, deletions, or modifications to this information at any time without prior notification. Rev 02.20

**SIMONA PMC**  
 2040 Industrial Drive  
 Findlay, OH 45839  
 T: 877.289.7626  
 F: 419.425.0501  
<https://simona-pmc.com/>