



Ontex® 8760

Description Ontex® 8760 is a directly paintable & bondable sheet system comprised of a thermoformable adhesion film layer (B side) laminated to a high melt strength, impact-modified, talc-filled TPO core and capped on the A side with PremierCap® high gloss TPO. The result is a product with all of the favorable properties of TPO plus enhanced melt strength as well as a high gloss, enhanced scratch & mar resistant cap and no need for surface preparation or special adhesives for B side bonding. Do not sand this product (will remove the film layer).

Applications Bumpers, wheel lips, valences, helms, industrial covers & enclosures

PROPERTY	TYPICAL VALUE ¹	UNITS	TEST METHOD
Specific Gravity	1.12		ISO 1183
Gloss, 60° (smooth, post-formed, male tooling)	85 - 90	%	ASTM 523
Crock Mar Resistance (Retained gloss at 60° observer)	75 - 80	%	PMC Method
Shrink Rate	0.8 – 1.0	%	ISO 294-4
Flexural Modulus	308,000 2,124	psi MPa	ASTM D790
Tensile Strength at Yield	2,740 18.9	psi MPa	ASTM D638
Gardner Impact at 32°F (0°C) at -22°F (-30°C)	320 (35.6) 208 (23)	in*lbs (Joules)	ASTM D5420
Multi-Axial Impact at 32°F (0°C) at -22°F (-30°C)	44.0, 100% ductile 32.4, 50% ductile	Joules	ASTM D3762
HDT at 66 psi (0.45 MPa) at 264 psi (1.45 MPa)	212 (100) 134 (57)	°F (°C)	ASTM D648
CLTE (-30°C to 80°C)	3.2 x 10 ⁻⁵ 5.8 x 10 ⁻⁵	in/in/°F mm/mm/°C	ISO 11359

Rev 04-21

NOTE: Data values are typical properties and are not to be construed as specifications. Users should confirm results by their own tests and evaluation methods. SIMONA PMC makes no warranties, expressed or implied, concerning the suitability of use. No freedom from infringement of any patent of others is to be inferred. SIMONA PMC reserves the right to make additions, deletions, or modifications to this information at any time without prior notification.

SIMONA PMC
 2040 Industrial Drive
 Findlay, OH 45839
 T: 877.289.7626
 F: 419.425.0501
www.simona-pmc.com