



PMC[®] 110

Description PMC[®] 110 is a high regrind, utility ABS sheet with a prime low gloss ABS cap.

Applications Interior components, shrouds, housings & claddings.

PROPERTY	TYPICAL VALUE ¹	UNITS	TEST METHOD
Specific Gravity	1.02 - 1.05		ISO 1183
Gloss, 60° (textured, post-formed, male tooling)	< 5	%	ASTM 523
Shrink Rate	0.4 – 0.8	%	ISO 294-4
Flexural Modulus	278,000 1,917	psi MPa	ASTM D790
Tensile Strength at Yield	3,887 – 5,802 27 - 40	psi MPa	ASTM D638

* Textured gloss noted. Color & Texture can affect post-formed gloss rating.

NOTE: Data values are typical properties and are not to be construed as specifications. Users should confirm results by their own tests and evaluation methods. SIMONA PMC makes no warranties, expressed or implied, concerning the suitability of use. No freedom from infringement of any patent of others is to be inferred. SIMONA PMC reserves the right to make additions, deletions, or modifications to this information at any time without prior notification. Rev. 04.20

SIMONA PMC
2040 Industrial Drive
Findlay, OH 45839
T: 877.289.7626
F: 419.425.0501
www.simona-pmc.com